

PR-1775 Class B non-chromate corrosion inhibitive sealant

Description

PR-1775 Class B is a non-chromate, corrosion inhibitive sealant. It has a service temperature range from -65°F (-54°C) to 250°F (121°C), with intermittent excursions up to 300°F (149°C). This material acts as an effective barrier against the common causes of corrosion on aluminum alloys or between dissimilar metals. The cured sealant maintains excellent elastomeric properties after exposure to both jet fuel and aviation gas.

PR-1775 Class B is a two-part, manganese dioxide cured, Permapo® P-5 polysulfide compound. The uncured material is a low sag, thixotropic paste suitable for application by extrusion gun or spatula. It cures at room temperature to form a resilient sealant having excellent adhesion to common aircraft substrates.

The following tests are in accordance with AMS 3265 Class B specification test methods.

Application properties (typical)

Color			
Part A	Black		
Part B	White		
Mixed	Gray		
Mixing ratio, By weight			
B-1/2	12:100		
B-2	10:100		
Base viscosity (Brookfield #7 @ 2 rpm), Poise (Pa-s)			
	11,000 (1100)		
Slump, inches (mm)			
	Initial	50 Minutes	90 Minutes
B-1/2	0.15 (3.81)	—	—
B-2	0.10 (2.54)	0.20 (5.08)	0.30 (7.62)
Application life and cure time @ 77°F (25°C), 50% RH			
	Application life (hours)	Tack free time (hours)	Cure time to 30 A Durometer (hours)
B-1/2	1/2	<5	20
B-2	2	<24	48

Performance properties (typical)

Cured 14 days @ 77°F (25°C), 50% RH	
Cured specific gravity	1.59
Nonvolatile content, %	94
Ultimate cure hardness, Durometer A	51
Peel strength, pli (N/25 mm), 100% cohesion	
AMS 2629 JRF immersion, 7 days @ 140°F (60°C)	
AMS 2471 (Anodized aluminum)	37 (165)
AMS 4901 (Titanium)*	34 (151)
AMS 5516 (Stainless steel)*	32 (142)
MIL-C-5541 (Alodine aluminum)	35 (156)
MIL-C-27725 (IFT coating)	33 (147)
AMS 2629 JRF/NaCl-H ₂ O immersion, 7 days @ 140°F (60°C)	
AMS 2471 (Anodized aluminum)	38 (169)
AMS 4901 (Titanium)*	40 (178)
AMS 5516 (Stainless steel)*	43 (191)
MIL-C-5541 (Alodine aluminum)	43 (191)
MIL-C-27725 (IFT coating)	38 (169)
*Primed with PR-148 Adhesion Promoter	
Tensile strength, psi (KPa)	
Standard cure, 14 days @ 77°F (25°C), 50% RH	
	495 (3413)
12 days immersion in AMS 2629 JRF @ 140°F (60°C)	
	500 (3448)
Elongation, %	
Standard cure, 14 days @ 77°F (25°C), 50% RH	
	420
12 days immersion in AMS 2629 JRF @ 140°F (60°C)	
	290
Corrosion test by cyclic loading and exposure - No signs of corrosion or sealant deterioration.	
Corrosion test by galvanic cell method, 1 week	
AMS 4045 Aluminum/AMS 4911 Titanium couple, - No signs of corrosion or sealant deterioration.	
AMS 4045 Aluminum/AMS 2400 Cadmium couple, - No signs of corrosion or sealant deterioration.	
Thermal rupture resistance - Retains pressure of 10 psi with only negligible deformation, both before and after immersion in AMS 2629 JRF.	
Low temperature flexibility @ -65°F (-54°C) - No cracking, checking or loss of adhesion.	

PR-1775 Class B non-chromate corrosion inhibitive sealant

Resistance to hydrocarbons - 7 days @ 140°F (60°C)
immersed in AMS 2629 JRF.

Weight loss, %	5.0
Swell, %	6.6

Paintability - No separation from sealant.

Flexibility - No cracks after bending 180 degrees over
0.125 inch (3.18 mm) mandrel.

Repairability to itself - Excellent to both freshly cured
as well as fuel aged and abraded fillets.

Fungus resistance Non-nutrient

Shaving and sanding - No rolling or tearing

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Surface preparation

Immediately before applying sealant to primed substrates, the surfaces should be cleaned with solvents. Contaminants such as dirt, grease, and/or processing lubricants must be removed prior to sealant application.

A progressive cleaning procedure should be employed using appropriate solvents, and a new lint free cloth conforming to AMS 3819. (reclaimed solvents or tissue paper should not be used).

Always pour solvent on the cloth to avoid contaminating the solvent supply. Wash one small area at a time.

It is important that the surface is dried with a second clean cloth prior to the solvent evaporating to prevent the redeposition of contaminants on the substrate.

Substrate composition can vary greatly. This can affect sealant adhesion. It is recommended that adhesion characteristics to a specific substrate be determined prior to application on production parts or assemblies.

For a more thorough discussion of proper surface preparation, please consult the SAE Aerospace Information Report AIR 4069. This document is available through SAE, 400 Commonwealth Avenue, Warrendale, PA 15096-0001.

U.S. Patent 4,623,711

Permapol is a trademark of PRC-DeSoto International, Inc., registered with the U.S. Patent Office.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

Printed in U.S.A.

Packaging Options

PR-1775 Class B is supplied in two-part can kits, Semco cartridges, and pre-mixed and frozen Semco cartridges.

Mixing instructions

Mix according to the ratios indicated in the application properties section. Mix Part A and Part B separately to uniformity, then thoroughly mix entire contents of both parts of kit together taking care to avoid leaving unmixed areas around the sides or bottom of the mixing container.

Storage life

The storage life of PR-1775 Class B is at least 9 months when stored at temperatures below 80°F (27°C) in original unopened containers.

The storage life of PR-1775 Class B in pre-mixed and frozen Semco cartridges is at least 30 days when stored at temperatures below -40°F (-40°C).

Health precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

**For emergency medical information call
1-800-228-5635.**

**Additional information can be found at:
www.ppgaerospace.com**

**For sales and ordering information call
1-800-AEROMIX (237-6649).**