



BOBBIN YARN

P&QC: _____
 Marketing: _____

ECK 18 1/0 0.7Z 610/53 bbn
EC13 272 Z28 610/53 bbn

PROPERTIES		INDIVIDUAL PACKAGE	LOT	PACKAGE INFORMATION	
Binder --	Type	610		PPG Bobbin Type	53
	% Nominal LOI %	0.95%	0.95%	Splices	Splice Free
	% Tolerance LOI %	+/- 0.30%	+/- 0.07%	Transfer Tails	Tie-on-Tails Available
				Nominal Weight of Full Package	19.1 Lbs/8.7 kg
Yardage --	Bare Glass, Nominal	1800 Yds/276 Tex	1800 Yds/276 Tex	Minimum Package Weight	10.0 Lbs/4.5 kg
	With Binder, Nominal	1781 Yds/278 Tex	1781 Yds/278 Tex	Package Weight Classification Supplied	SFP
	% Tolerance	+/- 6.0%	+/- 2.0%		ROM
	% COV, Nominal		2.00%		
	% COV, Maximum		2.90%	Minimum Metered Bobbin Length	
				Breakdown by Bobbin Size Each Shipment	Contact PPG Customer Service
Broken Filaments Per Plane, Maximum		10.0			
% Moisture Content Maximum		0.25%	0.20%		
Tensile Strength, Minimum		24.0 Lbs/107 Newtons			
Twist --	Turns per Inch	+/- 0.20 tpi			
Tolerance --	Turns per Meter	+/- 8 tpm			

OTHER: Conforms to ASTM D578 test method for fiber glass yarns. Lot average - N = 28