



No.: 3.27  
 Date: 11/1/99  
 Supersedes: All Previous

## TEXTURED TEXTILE YARNS

P&QC: \_\_\_\_\_  
 Marketing: \_\_\_\_\_

**ETDE 11.6 TEXO**  
**ET6 430 TEXO**

PROPERTIES	INDIVIDUAL PACKAGE			LOT			PACKAGE INFORMATION	
	NS	OS1	OS3	NS	OS1	OS3		
% Binder L.O.I.							Package Weight, Maximum	30.0 Lbs/13.6 Kg
With Overspray, Nominal		2.00%			2.00%		Minimum	2.0 Lbs/0.9 Kg
% Tolerance L.O.I.		+/- 0.60			+/- .12			
							Tie-On-Tails	Available on Request
Yardage -- (Yds/Tex)Bare Glass, Nominal		1200/413			1200/413			
With Overspray, Nominal		1176/422			1176/422		Tubes, Type	Paper
% Tolerance		+/- 5.5%			+/- 1.1%		Dimensions	13"/33 CM x 3.95"/10 CM (O.D.)
% COV, Nominal					1.45%			
% COV, Maximum					2.20%		Outside Diameter, Full Package	12.0 Inches/30.5 CM
Tensile Strength, Minimum (Lbs/Nt)		15/67					Packages/Carton	36
							Cartons/Pallet	1

**OTHER: Conforms to ASTM D578 test method for fiber glass yarns.**