



Q1300 SERIES AIR DRY ACRYLIC ENAMEL AEROSOLS

DESCRIPTION:

Fast dry exterior grade acrylic enamel aerosols that will adhere to most substrates and previously painted surfaces matched to your color and gloss specifications.

HIGHLIGHTS:

- ❖ Topcoat – Air dry or low temperature cure
- ❖ For use on bare metal or painted surfaces

PHYSICAL PROPERTIES (BLENDED):

PROPERTY	VALUE
Weight per gallon	6.00 – 9.60 lbs / gallon
Theoretical Coverage	800 mil SQ FT/GAL average
Adhesion	100% after 72 hours to most substrates
Flash Point	80°F - 100°F
Volume Solids	30% - 40%
Weight Solids	35% - 55%
VOC Content	4.0 lbs/gal – 5.0 lbs/gal
Storage Temperature	Minimum 20°F, Maximum 100°F
Shelf Life	12 months at recommended storage temperatures
Application Temperature	Minimum 60°F, Maximum 85°F

SURFACE PREPARATION:

The surface must be clean and free of oil, grease, and other contaminants. For best application properties, paint should be above 68°F before application.

CURE SCHEDULE:

Dry to touch: 15 minutes
 Dry to handle: 60 minutes
 Dry through: 24 hours
 To recoat: Before 60 minutes or after 72 hours

CONTACT 1-866-PPG TRUE

The technical data presented in this bulletin is based upon information believed by PPG to be currently accurate. However, no guarantees of accuracy, comprehensiveness or performance are given or implied. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin.

