



# PPG Coil Coatings Product Data Sheet

PPG INDUSTRIES, INC., COATINGS AND RESINS, 125 COLFAX STREET, SPRINGDALE, PENNSYLVANIA 15144

Product: TRUFORM® ZT

Location: Springdale, PA

Suggested Use: A thermosetting polyester paint designed for roll-coat application over properly cleaned, pretreated and primed Hot Dip Galvanized, GALVALUME®, Aluminum or CRS. TRUFORM ZT is designed for use in applications requiring high degrees of flexibility, moderate durability and low cost. Do not use for applications requiring dry heat, boiling water resistance or deep draw applications (TRUDRAW is recommended for these applications).

## PRODUCT DESCRIPTION (As Shipped)

Viscosity: 25 to 30 Sec.# 4 Zahn cup@ 77°F (25°C)

Flash Point 90°F (32.2°C) (Pensky-Martens)

Wt/Gal. 8.5-12.5 lbs/gallon (Kg./Lit. 1.01 - 1.50 kg.)

VOC # / Gal = 3.4 - 4.3 (0.40 - 0.52 kg/lit.)

Theor. Solids by Wt % 51-72 +/- 2.00

Contains Lubricant No

Theor. Solids by Vol % 43-54 +/- 1.50

## PHYSICAL PROPERTIES

Gloss: 5-80+ @ 60° / N/A @ 85°

Hardness: F-2H Eagle Turquoise

Film Thickness: As required Dry

Cure Test: 100+ Double MEK Rubs\*

Reverse Impact: \*\* 1½X MT:NPO aluminum  
3X MT:NPO steel on 23 guage (.027")

Flexibility: \*\*0T NPO aluminum, CRS  
1T NPO HDG, Galvalume

## SUGGESTED APPLICATION DATA

Substrate: Aluminum, HDG, Galvalume, CRS

Reducer: Butyl Cellosolve or Solvesso 150

Surface Preparation: As required

Clean Up: MEK

Primer:

Coverage/Gal: 920-1165 Sq. Ft. @ 0.75 Mils  
Coverage/Lit.: 85 - 109 m<sup>2</sup> @ 19.05 Microns

## LABORATORY CURE\*

Peak Metal Temperature 435°F-465°F Oven Temp. As Required  
(224-241°C)

Substrate Time At Temperature 5-10 seconds

*\*Peak metal temperature may vary due to dwell time. Line oven temperature and dwell time must be correlated with laboratory cure schedule.*

Additional Information: Peak metal temperature may vary due to dwell time. Six month shelf life from date of shipment.

\*\*Results will vary with metal thickness and temper.

\*MEK rubs will be lower if DFT is less than 0.65 mil and also if applied over B-902 CRS when no primer is present.

NOTE: Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. However, procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance or results, nor does PPG Industries, Inc. warrant freedom from patent infringement in the use of any formula or process set forth herein.