



## Q2300 SERIES AIR DRY LACQUER AEROSOLS

**DESCRIPTION:**

Fast dry nitrocellulose lacquer that adheres to most substrates and topcoats.

**HIGHLIGHTS:**

- ❖ Topcoat – Air dry
- ❖ For use on bare metal or painted surfaces
- ❖ Flat to high gloss
- ❖ Smooth or textured finish

**PHYSICAL PROPERTIES (BLENDED):**

PROPERTY	VALUE
Weight per gallon	7.70 – 9.20 lbs / gallon
Theoretical Coverage	800 mil SQ FT/GAL average
Adhesion	100% after 72 hours to most substrates
Flash Point	20°F - 40°F
Volume Solids	20% - 25%
Weight Solids	25% - 40%
VOC Content	5.0 lbs/gal – 5.8 lbs/gal
Storage Temperature	Minimum 20°F, Maximum 100°F
Shelf Life	12 months at recommended storage temperatures
Application Temperature	Minimum 45°F, Maximum 100°F

**SURFACE PREPARATION:**

The surface must be clean and free of oil, grease, and other contaminants. For best application properties, paint should be above 60°F before application.

**CURE SCHEDULE:**

- Dry to touch: 10 minutes
- Dry to handle: 30 minutes
- Dry through: 6 hours
- To recoat: Anytime

**CONTACT 1-866-PPG TRUE**

The technical data presented in this bulletin is based upon information believed by PPG to be currently accurate. However, no guarantees of accuracy, comprehensiveness or performance are given or implied. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin.

