



No.: 3.14  
 Date: 11/1/99  
 Supersedes: All Previous

## TEXTURED TEXTILE YARNS

P&QC: \_\_\_\_\_  
 Marketing: \_\_\_\_\_

**ETG 2.7 TEXO**  
**ET9 1835 TEXO**

PROPERTIES	INDIVIDUAL PACKAGE			LOT			PACKAGE INFORMATION	
	NS	OS1	OS3	NS	OS1	OS3		
% Binder L.O.I.							Package Weight, Maximum	25.0 Lbs/11.4 Kg
With Overspray, Nominal	1.10%	3.50%		1.10%	3.50%		Minimum	2.0 Lbs/0.9 Kg
% Tolerance L.O.I.	+/- 0.30%	+/- 1.25%		+/- 0.06%	+/- 0.25%			
							Tie-On-Tails	Available on Request
Yardage -- (Yds/Tex)Bare Glass, Nominal	271/1837	271/1837		271/1837	271/1837			
With Overspray, Nominal	N/A	267/1858		N/A	267/1858		Tubes, Type	Paper
% Tolerance	+/- 5.5%	+/- 5.5%		+/- 0.8%	+/- 0.8%		Dimensions	13"/33 CM x 3.95"/10 CM (O.D.)
% COV, Nominal				1.40%	1.40%			
% COV, Maximum				2.10%	2.10%		Outside Diameter, Full Package	12.0 Inches/30.5 CM
Tensile Strength, Minimum (Lbs/Nt)	38/169	36/160					Packages/Carton	36
							Cartons/Pallet	1

**OTHER: Conforms to ASTM D578 test method for fiber glass yarns.**