



BOBBIN YARN

P&QC: _____
 Marketing: _____

ECDE 75 1/0 1.0Z 207/53 bbn
EC6 68 Z40 207/53 bbn

PROPERTIES		INDIVIDUAL PACKAGE	LOT	PACKAGE INFORMATION	
Binder --	Type	207		PPG Bobbin Type	53
	% Nominal LOI %	0.40%	0.40%	Splices	Splice Free
	% Tolerance LOI %	+/- 0.18%	+/- 0.04%	Transfer Tails	Tie-on-Tails Available
				Nominal Weight of Full Package	18.4 Lbs/8.3 kg
Yardage --	Bare Glass, Nominal	7500 Yds/66 Tex	7500 Yds/66 Tex	Minimum Package Weight	6.0 Lbs/2.7 kg
	With Binder, Nominal	7463 Yds/66 Tex	7463 Yds/66 Tex	Package Weight Classification Supplied	SFP
	% Tolerance	+/- 7.0%	+/- 1.3%		ROM
	% COV, Nominal		2.30%		
	% COV, Maximum		3.30%	Minimum Metered Bobbin Length	
				Breakdown by Bobbin Size Each Shipment	Contact PPG Customer Service
Broken Filaments Per Plane, Maximum		10.0			
% Moisture Content Maximum		0.25%	0.20%		
Tensile Strength, Minimum		6.5 Lbs/29 Newtons			
Twist --	Turns per Inch	+/- 0.30 tpi			
Tolerance --	Turns per Meter	+/- 12 tpm			

OTHER: Conforms to ASTM D578 test method for fiber glass yarns. Lot average - N = 28