



No.: 3.13
 Date: 11/1/99
 Supersedes: All Previous

TEXTURED TEXTILE YARNS

P&QC: _____
 Marketing: _____

ETG 1.75 TEXO
ET9 2835 TEXO

PROPERTIES	INDIVIDUAL PACKAGE			LOT			PACKAGE INFORMATION	
	NS	OS1	OS3	NS	OS1	OS3		
% Binder L.O.I.							Package Weight, Maximum	25.0 Lbs/11.4 Kg
With Overspray, Nominal	1.10%	3.50%		1.10%	3.50%		Minimum	2.0 Lbs/0.9 Kg
% Tolerance L.O.I.	+/- 0.30%	+/- 1.25%		+/- 0.06%	+/- 0.25%			
							Tie-On-Tails	Available on Request
Yardage -- (Yds/Tex) Bare Glass, Nominal	175/2835	175/2835		175/2835	175/2835			
With Overspray, Nominal	N/A	167/2935		N/A	167/2935		Tubes, Type	Paper
% Tolerance	+/- 5.8%	+/- 5.8%		+/- 0.8%	+/- 0.8%		Dimensions	13"/33 CM x 3.95"/10 CM (O.D.)
% COV, Nominal				1.30%	1.30%			
% COV, Maximum				2.00%	2.00%		Outside Diameter, Full Package	12.0 Inches/30.5 CM
Tensile Strength, Minimum (Lbs/Nt)	65/289	63/280					Packages/Carton	36
							Cartons/Pallet	1

OTHER: Conforms to ASTM D578 test method for fiber glass yarns.