



MetalMax-Int/Ext Gloss Alkyd 914 series

MetalMax is a single component interior/exterior gloss alkyd enamel that is ideal for use on prepared metal substrates. Fully 3.5 VOC compliant, MetalMax is easy to apply, possesses durable gloss finish and offers full color capability through our Voice of Color.



B E N E F I T S

- ¥ Full Color tinting Capability with Voice of Color™ color system
- ¥ Durable interior /exterior gloss finish
- ¥ Fully VOC compliant
- ¥ Easy Application- Brush, Roll or Spray

MetalMax-Int/Ext Gloss Alkyd 7-914 Series

TECHNICAL DATA

Recommended Uses

Aluminum, Ferrous Metal,
Properly Primed Galvanized Steel

Compatible Undercoats

Aluminum 6-204, 90-712
Ferrous Metal 6-208,6-212,90-712
Galvanized Steel 90-712, 6-209

Gloss Level

80 to 100 (60° Gloss Meter)

Dry Time @ 77 Degrees F.

To Touch: 3 Hours
To Handle: 5 Hours
To Recoat: 24 Hours

Mixed VOC*

3.09lbs/gal 370.00g/L

Volume Solids

52% +/- 2%

Weight Solids

65% +/- 2%

Recommended Wet and Dry Film Thickness

1.5 minimum to 2.0 maximum

Theoretical Coverage

417 to 556 sq ft/gal (38 to 51sq. m/3.78L)

Thinning

DO NOT THIN

Mixing Instructions

Stir thoroughly before using and occasionally when in use.
When using more than one can of the same color, mix
together (box) before applying.



PRODUCT SELECTION GUIDE

PRODUCT CODE	DESCRIPTION	FIVE GALLON	ONE GALLON
7-914	Pastel Base	✓	✓
7-915	Midtone Base	✓	✓
7-916	Deeptone Base	✓	✓
7-917	Deep Rustic Base	✓	✓

For strictly regulated VOC markets or the most current technical data, check the technical data sheet on the website or phone number listed below.



The Evolution of High Performance

PPG Architectural Finishes, Inc.

One PPG Place • Pittsburgh, PA 15272 • 1-800-441-9695 • Fax: 888-807-5123 • www.ppghpc.com

PPG Canada Inc.

4 Kenview Boulevard • Brampton, ON L6T 5E4 • Phone: 905-790-5349 • Fax: 877-238-6441