



No.: 3.29  
 Date: 11/1/99  
 Supersedes: All Previous

## TEXTURED TEXTILE YARNS

P&QC: \_\_\_\_\_  
 Marketing: \_\_\_\_\_

**ETDE 25.0 TEXO  
 ET6 200 TEXO**

PROPERTIES	INDIVIDUAL PACKAGE			LOT			PACKAGE INFORMATION
	NS	OS1	OS3	NS	OS1	OS3	
% Binder L.O.I.							Package Weight, Maximum
With Overspray, Nominal		1.70%			1.70%		Minimum
% Tolerance L.O.I.		+/- .50			+/- .10		25.0 Lbs/11.4 Kg
							2.0 Lbs/0.9 Kg
							Tie-On-Tails
Yardage -- (Yds/Tex) Bare Glass, Nominal		2426/204			2426/204		Available on Request
With Overspray, Nominal		2383/208			2383/208		Tubes, Type
% Tolerance		+/- 5.5%			+/- 1.1%		Dimensions
% COV, Nominal					1.55%		13"/33 CM x 3.95"/10 CM (O.D.)
% COV, Maximum					2.30%		Outside Diameter, Full Package
							12.0 Inches/30.5 CM
Tensile Strength, Minimum (Lbs/Nt)		6/27					Packages/Carton
							36
							Cartons/Pallet
							1

**OTHER:** Conforms to ASTM D578 test method for fiber glass yarns.