



No.: 3.17  
 Date: 11/1/99  
 Supersedes: All Previous

## TEXTURED TEXTILE YARNS

P&QC: \_\_\_\_\_  
 Marketing: \_\_\_\_\_

**ETG 5.0 TEXO**  
**ET9 990 TEXO**

PROPERTIES	INDIVIDUAL PACKAGE			LOT			PACKAGE INFORMATION	
	NS	OS1	OS3	NS	OS1	OS3		
% Binder L.O.I.							Package Weight, Maximum	27.0 Lbs/12.3 Kg
With Overspray, Nominal	1.10%	3.50%		1.10%	3.50%		Minimum	2.0 Lbs/0.9 Kg
% Tolerance L.O.I.	+/- 0.30%	+/- 1.25%		+/- 0.06%	+/- 0.25%			
							Tie-On-Tails	Available on Request
Yardage -- (Yds/Tex) Bare Glass, Nominal	505/982	505/982		505/982	505/982			
With Overspray, Nominal	N/A	476/1027		N/A	476/1027		Tubes, Type	Paper
% Tolerance	+/- 5.5%	+/- 5.5%		+/- 1.1%	+/- 1.1%		Dimensions	13"/33CM x 3.95"/10 CM (O.D.)
% COV, Nominal				1.60%	1.60%			
% COV, Maximum				2.40%	2.40%		Outside Diameter, Full Package	12 Inches/30.5 CM
Tensile Strength, Minimum (Lbs/Nt)	20/89	20/89					Packages/Carton	36
							Cartons/Pallet	1

**OTHER:** Conforms to ASTM D578 test method for fiber glass yarns.