



TEXTURED TEXTILE YARNS

ETDE 9.0 TEXO
ET6 550 TEXO

P&QC: _____
 Marketing: _____

PROPERTIES	INDIVIDUAL PACKAGE			LOT			PACKAGE INFORMATION	
	NS	OS1	OS3	NS	OS1	OS3		
% Binder L.O.I.							Package Weight, Maximum	25.0 Lbs/11.4 Kg
With Overspray, Nominal	0.45%		2.50%	0.45%		2.50%	Minimum	2.0 Lbs/0.9 Kg
% Tolerance L.O.I.	+/- .15		+/- .75	+/- .03		+/- .15	Tie-On-Tails	Available on Request
Yardage -- (Yds/Tex) Bare Glass, Nominal	911/543		898/552	911/545		898/552	Tubes, Type	Paper
With Overspray, Nominal	N/A		875/567	N/A		875/567	Dimensions	13"/33 CM x 3.95"/10CM (O.D.)
% Tolerance	+/- 5.5%		+/- 5.5%	+/- 1.1%		+/- 1.1%	Outside Diameter, Full Package	12 Inches/30.5 CM
% COV, Nominal				1.45%		1.45%		
% COV, Maximum				2.20%		2.20%		
Tensile Strength, Minimum (Lbs/Nt)	20/89		20/89				Packages/Carton	36
							Cartons/Pallet	1

OTHER: Conforms to ASTM D578 test method for fiber glass yarns.